

جدول مداخل ضخامت قطعه کار در آزمون های سفتی راکول

Minimum Thickness mm	Regular Rockwell			Rockwell Superficial					
	HRA 60 kg Brale	HRB 100 kg 1/16" Ball	HRC 150 kg Brale	HR15N 15 kg Brale	HR30N 30 kg Brale	HR45N 45 kg Brale	HR15T 15 kg 1/16" Ball	HR30T 30 kg 1/16" Ball	HR45T 45 kg 1/16" Ball
0.15	-	-	-	92	-	-	-	-	-
0.20	-	-	-	90	-	-	-	-	-
0.25	-	-	-	88	-	-	91	-	-
0.30	-	-	-	83	82	77	86	-	-
0.36	-	-	-	76	78.5	74	81	80	-
0.41	86	-	-	68	74	72	75	72	71
0.46	84	-	-	-	66	68	68	64	62
0.51	82	-	-	-	57	63	-	55	53
0.56	79	-	69	-	47	58	-	45	43
0.61	76	94	67	-	-	51	-	34	31
0.66	71	87	65	-	-	37	-	-	18
0.71	67	80	62	-	-	20	-	-	4
0.76	60	71	57	-	-	-	-	-	-
0.81	-	62	52	-	-	-	-	-	-
0.86	-	52	45	-	-	-	-	-	-
0.91	-	40	37	-	-	-	-	-	-
0.96	-	28	28	-	-	-	-	-	-
1.02	-	-	20	-	-	-	-	-	-

کوپا، تجهیزات آزمون خواص مواد

**KOOPA**